What is Claimed is:

1. A method for sealing a threaded assembly comprising:

providing a dispenser having a joint-sealing material packaged therein, wherein the joint-sealing material comprises a multifilament yarn and a joint-sealing composition ready coated over the yarn;

removing a portion of the joint-sealing material from the dispenser; and

applying the portion of the joint-sealing material to threads of a first threaded component of the threaded assembly.

2. The method of claim 1, wherein the first threaded component is a threaded male component.

3. The method of claim 1, wherein the first threaded component is a threaded pipe.

4. The method of claim 1, further comprising:

providing a second threaded component; and

screwing the second threaded component over the threads of the first threaded component.

5. The method of claim 4, wherein the second threaded component is a threaded female component.

6. The method of claim 1, wherein the step of removing a portion of the joint-sealing material from the dispenser further comprises:

pulling the portion of the joint-sealing material through an aperture of the dispenser of dispenser; and

closing the aperture with a closure means.

7. The method of claim 1, further comprising the step of cutting the portion of the joint-sealing material to separate the portion from joint-sealing material remaining in the dispenser.

8. The method of claim 1, wherein the joint-sealing composition is a non-curing paste.

9. The method of claim 8, wherein the joint-sealing composition comprises an oil and a filler, wherein the oil is selected from the group consisting of linseed oil, silicone oil, mineral oil, and combinations thereof.

10. The method of claim 8, wherein the filler is a calcium carbonate filler.

11. The method of claim 8, wherein the joint sealing composition has a viscosity from about 20,000 mPas to about 500,000 mPas

12. The method of claim 1, wherein the joint-sealing composition is a curable polymeric composition.

13. The method of claim 12, wherein the curable polymeric composition comprises a reactive monomer selected from the group consisting of a mono-functional acrylate ester, a poly-functional acrylate ester, a mono-functional methacrylate ester, a poly-functional methacrylate ester and combinations thereof.

14. The method of claim 12, wherein the joint-sealing composition comprises a hydroxyl-terminated polydimethyl siloxane and a filler.

15. The method of claim 12, wherein the joint-sealing composition further includes a filler.

16. The method of claim 1, wherein the yarn is a polyamide yarn or a polypropylene yarn.